



TapeCase Ltd.  
1982 Lunt Ave, Elk Grove Village, IL 60007  
phone: (847) 299-7880  
fax: (847) 299-7804  
www.tapecase.com  
sales@tapecase.com

# 3M

## PTFE Glass Cloth Tape

### 5453

**Product Description** 3M™ PTFE Glass Cloth Tape 5453 has a silicone adhesive which provides a high temperature release surface for protection and insulation.

Product Construction	Backing	Adhesive	Color
	Woven glass cloth impregnated with PTFE (polytetrafluoroethylene)	Silicone	Brown

#### Typical Physical Properties

**Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.**

		ASTM Test Method
<b>3M tape 5453</b>		
Adhesion to Steel:	55 oz./in. width (56 N/100 mm)	D-3330
Tensile Strength:	175 lbs./in. width (3065 N/100 mm)	D-3759
Backing Thickness:	6.0 mils (0.15 mm)	D-3652
Total Tape Thickness:	8.2 mils (0.21 mm)	D-3652
Temperature Use Range:	-100° to 400°F (-73° to 204°C)	

#### Features

- Moisture absorption is close to zero, allowing performance in many humid environments.
- The reinforcement provided by the woven glass cloth fabric base adds tensile strength and resistance to tear and puncture in comparison to typical PTFE film backed tapes.

**CAUTION:** When PTFE film tape is exposed to temperatures above 400°F (204°C), small quantities of hazardous vapors may be released. INHALATION OF THESE VAPORS MAY BE HARMFUL OR MAY CAUSE RESPIRATORY TRACT IRRITATION. Do not heat or expose PTFE film tape to temperatures above 400°F (204°C).



**TapeCase Ltd.**  
**1982 Lunt Ave, Elk Grove Village, IL 60007**  
**phone: (847) 299-7880**  
**fax: (847) 299-7804**  
**www.tapecase.com**  
**sales@tapecase.com**

---

<b>Application Ideas</b>	<ul style="list-style-type: none"><li>• Easy-release surface on packaging and heat sealing machines, ironing and pressing equipment.</li><li>• Release surface on bonding tools.</li><li>• Lining conveying chutes, troughs and ducts.</li><li>• Covering rollers, drums, tumblers and formers on stitchers, binders and other process machinery.</li></ul>
<b>Storage</b>	Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H. in the original carton.
<b>Shelf Life</b>	To obtain best performance, use this product within 18 months from date of manufacture.

---